



### JLW-315C

#### Double-Sided Bi-Directional Filament Tape

Physical Properties	Standard	Metric	Test Method	
Reinforcement	Fiberglass			
Adhesive	Acrylic Pressure-Sensitive Adhesive			
Backing	White Paper			
Color	White			
Total Thickness	12.5 mils	0.32 mm	ASTM D-3652	GB/T7125
Peel Adhesion 90°	43 oz/in	12 N/25 mm	ASTM D-3330	GB/T2792
Holding Power	12±3 h	12±3 h	ASTM D-3654	GB/T4851
Tensile strength	67 lbs/in	300 N/25 mm	ASTM D-3759	GB/T7753
Elongation at Break	5-7%	5-7 %	ASTM D-3759	GB/T7753
Service Tem.--Mini	23°F	-5°C	BC/BD-220SE	BC/BD-220SE
Service Tem.--Max	212°F	100°C	DHG-9055A	DHG-9055A

#### Description

JLW-315C is a high-strength, double-sided bidirectional fiber tape made with white kraft paper and glass fiber as the substrate. It adheres firmly even to rough surfaces, making it suitable for self-adhesive decorative components and specifically designed for bonding foam rubber door and window sealing strips.

#### Performance Features

JLW-315C is a white, high-strength, double-sided bidirectional fiber tape. The embedded glass fiber strands provide significantly greater tensile strength compared to conventional double-sided tapes. It uses a modified acrylic pressure-sensitive adhesive, ensuring strong and reliable bonding of door and window sealing strips, foam materials, and movable automotive components. The tape offers bidirectional reinforcement and firm adhesion, with excellent wear resistance, impact resistance, and long-lasting holding power.

#### Shelf Life

Up to one years from the date of shipment with proper storage.

#### Storage Condition

It is recommended to store the product in a clean, dry environment to prevent packaging damage. Avoid placing it near volatile solvents. The optimal storage temperature is between 39-79°F (4-26°C), with a relative humidity of 40%-50%. Rotate inventory regularly to maintain product quality.

The test results provided above represent average values obtained under laboratory conditions and are intended for general reference only. JL3 does not guarantee the accuracy, completeness, or performance consistency of these results. These values do not constitute a warranty, either express or implied, including but not limited to warranties of performance, safety, or fitness for a particular purpose—whether the product is used alone or in combination with other materials. JL3 strongly recommends that users conduct independent testing to determine the product's suitability for their specific application prior to use. JL3 assumes no liability for any damage, loss, or injury arising from the use of this product. All sales are subject to JL3's standard terms and conditions. Product specifications and information are subject to change without prior notice.

#### Fujian Jialong Adhesive Tape Co.,Ltd.

No. 11 Xiazhai Road, Jiulong Industrial Park, Hua An Economic Development Zone, Hua An, Zhangzhou, Fujian 363000 China.  
 Tel: +86 596-728-0001  
 info@jl3tape.com  
 http://www.jl3tape.com

