



## JLN-8152 White

### REINFORCED WATER-ACTIVATED TAPE

| Physical Properties      |   | Standard   | Metric     | Test Method |          |
|--------------------------|---|--|------------|-------------|----------|
| Color                    |   | White  |            |             |          |
| Laminating Adhesive      |   | Hot Melt Adhesive: 26 g/m <sup>2</sup>           |            |             |          |
| Water-Activated Adhesive |   | Starch Adhesive: 20 g/m <sup>2</sup>             |            |             |          |
| Total Thickness          |   | 5.1 mils   | 0.13 mm    | ASTM D-3652 | GB/T7125 |
| Tensile Strength         | MD  | 47 lbs/in  | 210 N/25mm | ASTM D-3759 | GB/T7753 |
|                          | CD  | 23 lbs/in  | 105 N/25mm | ASTM D-3759 | GB/T7753 |
| Reinforcement            | MD  | (1-1-1-1-1) 110 Fiberglass per 72mm              |            |             |          |
|                          | CD  | (1-1-1) 150 Fiberglass, 1" spacing, at 45° angle |            |             |          |
| Backing                  | Top Ply : 25 lb ( 39 g/m <sup>2</sup> ) White Virgin Paper (virgin fibers)    |  |            |             |          |
|                          | Bottom Ply : 25 lb ( 39 g/m <sup>2</sup> ) White Virgin Paper (virgin fibers) |  |            |             |          |

#### DESCRIPTION

JLN-8152 Water-activated reinforced kraft paper tape is a green environmental protection product, is the national and provincial new products, and its base material and adhesive will not cause pollution to the environment and can recycling use with the packaging. It is mainly used to replace pressure sensitive adhesive tape, etc. Used for carton sealing.

#### PRODUCT APPLICATION

Used for two strip sealing cartons top and bottom. Works well on recycled cartons, and non-unitized loads.

Recommended for use on light weight to average cartons up to **20 pounds (9 kg)**.

#### STORAGE CONDITION

It's recommended to store in clean and dry place. Damaged packaging shall be prevented. Not stored with volatile solvent. The temperature of storage shall be 4°C to 26°C and the humidity shall be between 40% and 50%. Rotate inventory recommended.

The above properties and results obtained refer to the average values of laboratory testing carried out on the samples of JIALONG product. JIALONG does not guarantee testing accuracy and makes no guarantee of product performance, safety, or suitability, either expressed or implied, when used alone or in combination with other products. JIALONG strongly urges users to undertake independent testing in order to verify the suitability of the product for whatever intended use. JIALONG assumes no responsibility for any damage or injury sustained as a result of the use of its products.

#### FUJIAN JIALONG ADHESIVE TAPE CO., LTD.

No.11 Xiazhai Road, Jiulong Industry Park, Hua An, Zhangzhou, Fujian 363000 China.  
Tel:+86-592-207-5506  
<http://www.jl3tape.com/>

